



ANUCRYL AC-540

TECHNICAL DATA SHEET

INTRODUCTION	ANUCRYL AC-540 is a pure acrylic emulsion which is self-cross linkable, stain and UV resistant. It is low VOC and formaldehyde free. It has excellent adhesion to metals also.																											
APPLICATION	ANUCRYL AC-540 is excellent adhesion to metals. It is useful for in maintenance metal coating and industrial coating.																											
KEY FEATURES	<ul style="list-style-type: none">• Self-cross linkable• Low VOC and formaldehyde free.• Excellent adhesion to metals																											
TYPICAL PROPERTIES	<table><tr><td>Appearance</td><td>:</td><td>Semi Translucent liquid</td></tr><tr><td>% Solid Content @150° C ; 1/2hr</td><td>:</td><td>49 ± 1</td></tr><tr><td>pH (As is)</td><td>:</td><td>9.0 - 10.0</td></tr><tr><td>Ford cup Viscosity 30°C</td><td>:</td><td>30 – 35 Sec</td></tr><tr><td>Glass Transition Temperature</td><td>:</td><td></td></tr><tr><td>Theoretical Tg [°C]</td><td>:</td><td>12</td></tr><tr><td>Film properties</td><td>:</td><td></td></tr><tr><td>Curing – At Room Temperature</td><td>:</td><td>24 hrs</td></tr><tr><td>At 80°C [accelarated curing]</td><td>:</td><td>10 minutes</td></tr></table>	Appearance	:	Semi Translucent liquid	% Solid Content @150° C ; 1/2hr	:	49 ± 1	pH (As is)	:	9.0 - 10.0	Ford cup Viscosity 30°C	:	30 – 35 Sec	Glass Transition Temperature	:		Theoretical Tg [°C]	:	12	Film properties	:		Curing – At Room Temperature	:	24 hrs	At 80°C [accelarated curing]	:	10 minutes
Appearance	:	Semi Translucent liquid																										
% Solid Content @150° C ; 1/2hr	:	49 ± 1																										
pH (As is)	:	9.0 - 10.0																										
Ford cup Viscosity 30°C	:	30 – 35 Sec																										
Glass Transition Temperature	:																											
Theoretical Tg [°C]	:	12																										
Film properties	:																											
Curing – At Room Temperature	:	24 hrs																										
At 80°C [accelarated curing]	:	10 minutes																										
SAFETY DATA	<p>Health Hazard: ANUCRYL AC-540 is alkaline in nature and harmful if swallowed. Avoid contact with skin. Use protective clothing, hand gloves, goggles, safety shoes etc., while handling this material. In case of contact or splash on eyes, wash with sufficient amount of water and consult a physician.</p> <p>Fire Hazard: ANUCRYL AC-540 is water-based and non-flammable.</p>																											
STORAGE	Store products in tightly closed original containers at temperatures recommended on the product label.																											
PACKAGING																												

240 Kg HDPE Drums/Tanker.

**HANDLING
PRECAUTION**

Before using this product, consult the Material Safety Data Sheet (MSDS) for details on product hazards, recommended handling precautions and product storage.

DISCLAIMER

This information is given to the best of our knowledge. There is no legally binding assurance of certain properties for a specific purpose. The customer is responsible for determining whether the product and Information provided here is appropriate for his use or not. It is the sole responsibility of the customer to ensure that any proprietary rights and existing laws and legislation are observed.

ANUVI CHEMICALS LIMITED (AN ISO 9001: 2015 COMPANY)

Sales office: 205/210/211, Narmada, Laxmi Industrial Premises,
Pokharan Road No.1, Vartak Nagar, Thane (W) - 400 606,
Maharashtra, India.

Tel.: +91-22-25855379 / 25855714 **Website** www.anuvi.in

