

ANUCRYL C-168

TECHNICAL DATA SHEET

INTRODUCTION	ANUCRYL C-168 is a styrene/ acrylic emulsion. It has excellent pigment loading characteristics, water and alkali resistance properties.																								
APPLICATION	ANUCRYL C-168 is used for Economic Distempers and Cement Primers.																								
TYPICAL PROPERTIES	<table border="0"> <tr> <td>Appearance</td> <td>:</td> <td>Milky white liquid</td> </tr> <tr> <td>% Solid Content</td> <td>:</td> <td>45 ± 1</td> </tr> <tr> <td>pH</td> <td>:</td> <td>8.0 – 10.0</td> </tr> <tr> <td>Brook Field Viscosity</td> <td></td> <td></td> </tr> <tr> <td>Spindle no. 3/ RPM 60@ 30°C</td> <td>:</td> <td>500 – 1000 Cps</td> </tr> <tr> <td>Glass Transition Temperature</td> <td></td> <td></td> </tr> <tr> <td>Theoretical Tg [°C]</td> <td>:</td> <td>26</td> </tr> <tr> <td>Film properties</td> <td>:</td> <td>Clear</td> </tr> </table>	Appearance	:	Milky white liquid	% Solid Content	:	45 ± 1	pH	:	8.0 – 10.0	Brook Field Viscosity			Spindle no. 3/ RPM 60@ 30°C	:	500 – 1000 Cps	Glass Transition Temperature			Theoretical Tg [°C]	:	26	Film properties	:	Clear
Appearance	:	Milky white liquid																							
% Solid Content	:	45 ± 1																							
pH	:	8.0 – 10.0																							
Brook Field Viscosity																									
Spindle no. 3/ RPM 60@ 30°C	:	500 – 1000 Cps																							
Glass Transition Temperature																									
Theoretical Tg [°C]	:	26																							
Film properties	:	Clear																							
SAFETY DATA	<p>Health Hazard: ANUCRYL C-168 is alkaline in nature and harmful if swallowed. Avoid contact with skin. Use protective clothing, hand gloves, goggles, safety shoes etc., while handling this material. In case of contact or splash on eyes, wash with sufficient amount of water and consult a physician.</p> <p>Fire Hazard: ANUCRYL C-168 is water-based and non-flammable.</p>																								
STORAGE	Store products in tightly closed original containers at temperatures recommended on the product label.																								
PACKAGING	240 Kg HDPE Drums/ Tanker.																								

**HANDLING
PRECAUTION**

Before using this product, consult the Material Safety Data Sheet (MSDS) for details on product hazards, recommended handling precautions and product storage.

DISCLAIMER

This information is given to the best of our knowledge. There is no legally binding assurance of certain properties for a specific purpose. The customer is responsible for determining whether the product and Information provided here is appropriate for his use or not. It is the sole responsibility of the customer to ensure that any proprietary rights and existing laws and legislation are observed.

ANUVI CHEMICALS LIMITED (AN ISO 9001: 2015 COMPANY)

Sales office: 205/210/211, Narmada, Laxmi Industrial Premises,
Pokharan Road No.1, Vartak Nagar, Thane (W) - 400 606,
Maharashtra, India.

Tel.: +91-22-25855379 / 25855714 **Website** www.anuvi.in

