

ANUCRYL HA-100

TECHNICAL DATA SHEET

<p>INTRODUCTION</p>	<p>ANUCRYL HA-100 is an associative thickener based on a hydrophobically modified alkali swellable emulsion (HASE) Chemistry. ANUCRYL HA-100 is swellable with alkali by associative mechanisms above pH of 8. It gives mid shear high viscosity. It is associative rheology modifier that provides low-cost, high performance alternative to cellulosic thickeners in interior flat, sheen and satin latex paint.</p>																					
<p>APPLICATION</p>	<p>ANUCRYL HA-100 can be used in structured paints and replace high molecular weight HEC in renders, plasters, etc. It is highly resistant to microbial attack.</p>																					
<p>NEUTRALIZATION</p>	<p>A minimum of approximately 0.1 kg of 28% aqueous ammonia or 0.15 kg of AMP-90 or 0.3 kg of NaOH at 20% is required to completely neutralize all the acid groups in a wet kg of product supplied at 30% solids. Additional base may be required to achieve the required final pH. When ANUCRYL HA-100 is neutralized with base, it shows increment in the viscosity. Thickening begins at about pH 6 and solubilization is essentially complete at pH 7.</p>																					
<p>TYPICAL PROPERTIES</p>	<table border="0"> <tr> <td>Appearance</td> <td>:</td> <td>Milky white liquid</td> </tr> <tr> <td>% Solid Content</td> <td>:</td> <td>30 ± 1</td> </tr> <tr> <td>pH (when packed)</td> <td>:</td> <td>2 – 4</td> </tr> <tr> <td>Brook Field</td> <td></td> <td></td> </tr> <tr> <td>Viscosity, Spindle no. 1/RPM 60@ 25^o C</td> <td>:</td> <td>< 50 Cps</td> </tr> <tr> <td>Specific Gravity @25^oC</td> <td>:</td> <td>1.05 – 1.07</td> </tr> <tr> <td>Mechanical stability</td> <td>:</td> <td>Good</td> </tr> </table>	Appearance	:	Milky white liquid	% Solid Content	:	30 ± 1	pH (when packed)	:	2 – 4	Brook Field			Viscosity, Spindle no. 1/RPM 60@ 25 ^o C	:	< 50 Cps	Specific Gravity @25 ^o C	:	1.05 – 1.07	Mechanical stability	:	Good
Appearance	:	Milky white liquid																				
% Solid Content	:	30 ± 1																				
pH (when packed)	:	2 – 4																				
Brook Field																						
Viscosity, Spindle no. 1/RPM 60@ 25 ^o C	:	< 50 Cps																				
Specific Gravity @25 ^o C	:	1.05 – 1.07																				
Mechanical stability	:	Good																				
<p>SAFETY DATA</p>	<p>Health Hazard: ANUCRYL HA-100 is acidic in nature and harmful if swallowed. Avoid contact with skin. Use protective clothing, hand gloves, goggles, safety shoes etc., while handling this material. In case of contact or splash on eyes, wash with enough water and consult a physician. Fire Hazard: ANUCRYL HA-100 is water-based and non-flammable.</p>																					
<p>STORAGE</p>	<p>Store products in tightly closed original containers at temperatures recommended on the product label.</p>																					

PACKAGING	240 Kg HDPE Drums/Tanker.
HANDLING PRECAUTION	Before using this product, consult the Material Safety Data Sheet (MSDS) for details on product hazards, recommended handling precautions and product storage.
DISCLAIMER	This information is given to the best of our knowledge. There is no legally binding assurance of certain properties for a specific purpose. The customer is responsible for determining whether the product and Information provided here is appropriate for his use or not. It is the sole responsibility of the customer to ensure that any proprietary rights and existing laws and legislation are observed.

ANUVI CHEMICALS LIMITED (AN ISO 9001: 2015 COMPANY)

Sales office: 205/210/211, Narmada, Laxmi Industrial Premises, Pokharan Road No.1, Vartak Nagar, Thane (W) - 400 606, Maharashtra, India.

Tel.: +91-22-25855379 / 25855714 **Website** www.anuvi.in

