



Technical Data Sheet

GOLD BRONZE POWDER

Pale Gold Super Lac

Trade Mark: A3

| Characteristics | UOM | *Test Method | Specification |
|------------------------------|--------------------|--------------|---------------|
| <u>Sieve analysis:</u> | | | |
| Passing through sieve 150 µm | % | M/QA/SOP/003 | 99.9 min |
| Passing through sieve 45 µm | % | M/QA/SOP/003 | 97 min |
| Passing through sieve 25 µm | % | M/QA/SOP/003 | 85 min |
| Leafing Power | % | M/QA/SOP/019 | 40 min |
| Water covering Capacity | cm ² /g | M/QA/SOP/020 | 3500 min |

*M/QA/SOP/003,M/QA/SOP/019 & M/QA/SOP/020 are based on ISO-1247

A3 Super Lac-type, Gold Bronze flake metal powder (Leafing)based on a high pure copper alloy (Brass) of approx 90 % Copper and 10 % Zinc, in a dry ball milling process,Pale Gold in shade and corn flake in shape, for the applications like Aerosol, Decorative coatings, Screen printing, Textile coatings etc

The data on this technical information sheet correspond with the current status of our knowledge and experience. The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights. We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process.

MEPCO

Thirumangalam,
Madurai
PIN: 625706
Tamilnadu,India
Phone: + 91 4549 280599
Fax: +91 4549 281273

E-mail:info@mepco.co.in
Web:www.mepco.co.in

Edition: 02.01.2023
Page 1 of 1