



# Technical Data Sheet

## GOLD BRONZE POWDER

### Rich Pale Gold Super Lac

Trade Mark: B3

Characteristics	UOM	*Test Method	Specification
<u>Sieve analysis:</u>			
Passing through sieve 150 µm	%	M/QA/SOP/003	99.9 min
Passing through sieve 45 µm	%	M/QA/SOP/003	97 min
Passing through sieve 25 µm	%	M/QA/SOP/003	85 min
Leafing Power	%	M/QA/SOP/019	40 min
Water covering Capacity	cm <sup>2</sup> /g	M/QA/SOP/020	3500 min

\*M/QA/SOP/003,M/QA/SOP/019 & M/QA/SOP/020 are based on ISO-1247

B3 Super Lac-type, Gold Bronze flake metal powder (Leafing)based on a high pure copper alloy (Brass) of approx 80 % Copper and 20 % Zinc, in a dry ball milling process, Rich Pale Gold in shade and corn flake in shape, for the applications like Aerosol, Decorative coatings, Screen printing, Textile coatings etc

*The data on this technical information sheet correspond with the current status of our knowledge and experience. The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights. We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process.*

## MEPCO

Thirumangalam,  
Madurai  
PIN: 625706  
Tamilnadu, India  
Phone: + 91 4549 280599  
Fax: +91 4549 281273

E-mail: info@mepco.co.in  
Web: www.mepco.co.in

Edition: 02.01.2023  
Page 1 of 1