

LEAFING STANDARD

LEAFING ALUMINIUM PASTE

Trade Mark: NA7512

Solvent: Naptha

Characteristics	UOM	Test Method	Specification
<u>Sieve analysis:</u> Residue on sieve 45µm	%	M/QA/SOP/003	1 – 3
Volatile Matter	%	M/QA/SOP/017	34 max
Non volatile matter	%	M/QA/SOP/017	66 min
Leafing power	%	ISO 1247-1	77 min
Water covering capacity	cm ² /g	ISO 1247-1	20000 - 23000
Matter soluble in organic solvent	%	M/QA/SOP/006	2 – 4

* M/QA/SOP/003, M/QA/SOP/017, M/QA/SOP/006 are based on ISO-1247.

NA 7512 Standard Leafing Aluminium Paste corn flake in shape, mineral spirit & high aromatic solvent naphtha as pasting agent, for the applications like Chrome finish coatings, Corrosion protection coatings, Decorative coatings, Exterior coatings with high reflectivity, General purpose coatings, Heat-resistant coatings, Industrial coatings, Spray paintings, Roof coating etc.

The data on this technical information sheet correspond with the current status of our knowledge and experience. The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights. We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process.

MEPCO