



Technical Data Sheet

GOLD BRONZE POWDER

Copper Gold Lac

Trade Mark: O2

Characteristics	UOM	*Test Method	Specification
<u>Sieve analysis:</u>			
Passing through sieve 150 µm	%	M/QA/SOP/003	99.5 min
Passing through sieve 45 µm	%	M/QA/SOP/003	85 min
Passing through sieve 25 µm	%	M/QA/SOP/003	55 min
Leafing Power	%	M/QA/SOP/019	30 min
Water covering Capacity	cm ² /g	M/QA/SOP/020	1700 min

*M/QA/SOP/003,M/QA/SOP/019 & M/QA/SOP/020 are based on ISO-1247

O2 Lac-type, Copper Gold flake metal powder (Leafing) based on a high pure copper powder, in a dry ball milling process, Copper Gold in shade and corn flake in shape, for the applications like Decorative coatings, Screen printing, Textile printings etc.

The data on this technical information sheet correspond with the current status of our knowledge and experience. The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights. We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process.

MEPCO

Thirumangalam,
Madurai
PIN: 625706
Tamilnadu, India
Phone: + 91 4549 280599
Fax: +91 4549 281273

E-mail: info@mepco.co.in
Web: www.mepco.co.in

Edition: 02.01.2023
Page 1 of 1