

15% POTASSIUM HEX-CEM



Accelerator additive for unsaturated polyesters
and pot life stabilizer for 2 components PUR systems

Description

15% POTASSIUM HEX-CEM is a potassium 2-ethylhexanoate dissolved in diethylen diglycol which combined with cobalt support the accelerating effect in unsaturated polyesters. This results in a decrease of discoloration of UPS-Systems caused by Cobalt.

Further it is also capable of stabilizing the rheological and the pot life behaviour of water-borne 2-components PUR systems and additionally it can positively affect the haze-values of these paint systems

Characteristic data

Metal content K, %	14.9 – 15.2	Borchers 08-K-03 (Acidimetry)
Density (20 °C), g/cm ³	1.09 – 1.13	DIN 53217(A) - 1991
Viscosity (20 °C), mPa·s:	3;000 – 6;000	ISO 3219 (A) - 1994
Water content, %:	3.0 – 4.5	DIN 51777 - 1974
Flash point, °C:	> 100 (typical)	ISO 3679 - 1991
Solvent:	diethylen diglycol	

Properties

15% POTASSIUM HEX-CEM is completely miscible with water, alcohols and other polar solvents. **15% POTASSIUM HEX-CEM** is hygroscopic and may therefore absorb moisture from the air. In the event of prolonged exposure to air, **15% POTASSIUM HEX-CEM** may react with carbon dioxide in the air (formation of carbonate). This is irrelevant if the product is handled correctly.

15% POTASSIUM HEX-CEM can be used as an accelerator in unsaturated polyester resins dissolved in styrene. Some cobalt carboxylate, for example, is still necessary although the required amount of cobalt can be reduced by using **15% POTASSIUM HEX-CEM**, permitting films or castings of a lighter colour.

15% POTASSIUM HEX-CEM is known to stabilize the pot life behaviour of water-borne 2-component PUR paints based on polyester resins. After addition of the catalyst, a uniform viscosity is obtained within the mixing time. This is an important criterion with spray application. Gloss and the surface properties of the paint film are also improved.

At the appropriate addition rate, a decrease in film hardness is unlikely to occur.

Applications

15% POTASSIUM HEX-CEM can be used in unsaturated polyesters such as in solvent-containing and water-borne systems.

15% POTASSIUM HEX-CEM



Dosage

The approximate dosage is 0.2 - 1.0 %, relative to total formulation.

The ideal dosage of **15% POTASSIUM HEX-CEM** could be considerably different for different field of application and has to be determined in trials for each system.

Storage

Protect from the effects of weathering and store at temperatures between 5 and 30 °C.
Once opened, containers should be resealed immediately after each removal of the product.

With prolonged storage of opened containers it is advisable to scavenge the vapour space above the product with nitrogen before resealing the containers.

Safety

Please refer to our safety data sheet for information relating to product safety.

Updated: 03.03.2009

OMG Borchers GmbH
Berghausener Str. 100 / 40764 Langenfeld / Telephone: +49 (0) 2173 – 39 26 666
Fax: +49 (0) 2173 – 39 26 999 / Internet: www.borchers.com / E-Mail: info.borchers@eu.omgi.com

Our product information is given in good faith but without warranty. This also applies where proprietary rights of third parties are involved. This information does not release the customer from the obligation to test our products as to their suitability for the intended processes and uses. The application, use and

processing of our products and the products manufactured by the customer on the basis of our technical advice are beyond our control and, therefore, entirely the customer's own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.
