



## Tin-free catalyst for solvent-borne two-component polyurethane coatings

### Description

**Borchi® Kat 0244** is a newly developed tin-free catalyst based on metal carboxylate that is used as an accelerator for solvent-borne two-component polyurethane coatings. **Borchi® Kat 0244** contains no organic complexing agents.

**Borchi® Kat 0244** is a non-hazardous replacement for other polyurethane catalysts, especially for tertiary amines and DBTL.

### Characteristic data

Appearance:	clear, colorless to yellow liquid	
Density (20 °C), g/cm <sup>3</sup> :	1.19 – 1.25	DIN 51757 (A) - 1994
Viscosity (20 °C), mPa·s:	1,000 – 6,000	ISO 3219 (A) - 1994
Colour, Gardner::	max. 6	ISO 4630 - 1981
Water content, %:	max. 0.5	DIN 51777 - 1974
Flash point, °C:	> 100	

### Properties

**Borchi® Kat 0244** accelerates the chemical reaction between the alcohol and isocyanate component of polyurethane coating systems, thus allowing optimum steering of the drying properties, both during force-drying and curing at room temperature.

The use of **Borchi® Kat 0244** ensures fast blocking stability of polyurethane coatings. Moreover improves solvent resistance, high film hardness and early sandability of the coating. **Borchi® Kat 0244** can be used as a replacement for dibutyl tin dilaurate (DBTL), in many systems yielding better properties, e.g. reduced yellowing and higher film hardness, than DBTL catalyzed systems.

### Applications

**Borchi® Kat 0244** is suitable for solvent-borne two-component polyurethane clear coats, e.g. for automotive refinishing. In pigmented coating systems, the catalytic activity may be reduced after prolonged storage. In such cases, we recommend the use of our product *Borchi® Kat 0245*.



---

## Use and Dosage

Our experience has shown the recommended addition rate of **Borchi® Kat 0244** to be between 0.01 and 0.03 % product, calculated on solid binder. The exact amount depends on the used binder and should be determined by means of preliminary trials.

**Borchi® Kat 0244** can be added as supplied or solved in any suitable solvent (e.g. 10 % in xylene) to the polyol component of the coating system. The solution has to be homogenized by stirring. **Borchi® Kat 0244** is also soluble in polar solvents and solvents of medium polarity. However, these solutions are only stable for a limited period of time.

---

## Storage

Protect from the effects of weathering and store at temperatures between 5 and 30 °C.  
Once opened, containers should be resealed immediately after each removal of the product.

---

## Safety

Please refer to our safety data sheet for information relating to product safety.

Updated: 25.08.2009

---

**OMG Borchers GmbH**

Berghausener Str. 100 / 40764 Langenfeld / Telephone: +49 (0) 2173 – 39 26 666  
Fax: +49 (0) 2173 – 39 26 999 / Internet: [www.borchers.com](http://www.borchers.com) / E-Mail: [info.borchers@eu.omgi.com](mailto:info.borchers@eu.omgi.com)

---

Our product information is given in good faith but without warranty. This also applies where proprietary rights of third parties are involved. This information does not release the customer from the obligation to test our products as to their suitability for the intended processes and uses. The application, use and

processing of our products and the products manufactured by the customer on the basis of our technical advice are beyond our control and, therefore, entirely the customer's own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.