



Organo-modified silicone copolymer,
50 % active ingredient in methoxy propyl acetate

Description

Borchi® Gol LA 30 is a pre-diluted, highly efficient organo-modified silicone compound to improve surface properties during and after application. Flow and levelling properties will be positively influenced and formation of pin holes and craters will be reduced.

Borchi® Gol LA 30 develops a strong surface tension reduction and can be used either for clear-coats or for pigmented coating systems.

Characteristic data

Appearance:	clear liquid	
Active ingredient:	50 %	
Density (20 °), g/cm ³ :	approx. 0.98	DIN 51757
Viscosity (23 °C), s:	max. 25	DIN 53211
Refracting index (23 °C):	1.423 – 1.428	DIN 51423

Properties

Borchi® Gol LA 30 facilitates spreading and wetting characteristics to a wide range of formulated systems. The formation of surface defects like cratering, pin holes or Bénard cells will be inhibited.

Borchi® Gol LA 30 promotes the optical film appearance.

Applications

Borchi® Gol LA 30 is characterized by good binder compatibility and is particularly suitable for chemically curing finishing paints based on hydroxyl bearing polyacrylates and polyesters (e.g. range *Desmophen*® served by Bayer Material Science), primarily polyester melamine, epoxy and certain UV systems.

Borchi® Gol LA 30 furthermore controls levelling in physically curing finishes based on polyurethane and polyacrylate resin binders.



Dosage

Borchi® Gol LA 30 can be added to the paint in any formulation step including post addition. We recommend its addition in a final production step after adding all coating ingredients.

The required amount of **Borchi® Gol LA 30** depends on the required effect. Usual amounts are approx. 0.1 to 0.5 % by weight on total formulation. The optimum amount should be determined individually by pre-trials. When preparing pigmented systems, occasionally higher amounts are needed.

Storage

Protect from the effects of weathering and store at temperatures between 5 and 30 °C.
Once opened. Containers should be released immediately after each removal of the product.

Safety

Please refer to our safety data sheet for information relating to product safety.

Updated: 06.04.2009

OMG Borchers GmbH

Berghausener Str. 100 / 40764 Langenfeld / Telephone: +49 (0) 2173 – 39 26 666
Fax: +49 (0) 2173 – 39 26 999 / Internet: www.borchers.com / E-Mail: info.borchers@eu.omgi.com

Our product information is given in good faith but without warranty. This also applies where proprietary rights of third parties are involved. This information does not release the customer from the obligation to test our products as to their suitability for the intended processes and uses. The application, use and

processing of our products and the products manufactured by the customer on the basis of our technical advice are beyond our control and, therefore, entirely the customer's own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.